



**STYLE 1940 PWT
Urethane Coated Fabric to meet ATPD 2265
Specifications**

	Standard
Thickness - in. ASTM D-751	40 Mil
Base Fabric -Type - Weight	Nylon 13.0 oz./yd ²
Coating Finished Coated Weight ASTM D-751	Polyether Polyurethane 35.0 – 62.0 oz./yd ²
Tongue Tear ASTM D-751 3" x 8" sample size	35/35 lbs.
Strip Tensile ASTM D-751 Cut Strip Method	500/500 lbs./in.
Adhesion (min) ASTM D-751 Dielectric	30 lbs./in.
Low Temperature ASTM D-2136 1" Mandrel 4 hrs	Pass @ -50° F.
Puncture Resistance ASTM D-751	200 lbs.
Dead Load Seam Strength 200° F./93° C	2" overlap seam 100 lbs./in.

This is to certify that the internal coating compound is in compliance with the requirements of ANSI/NSF 61.

We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information. In case of conflict between standard and metric specifications, standard shall apply.

January, 2001