

Chemical Resistance

No	Chemical	DREAMLINER 30	DREAMLINER 28
1	Acetic acid (5%)	A	A
2	Acetic acid (50%)	C	C
3	Acetone (99.5%)	C	C
4	CASTM #1 oil	A	A
5	ASTM #2 oil	A	A
6	ASTM #3 oil	A	A
7	Ammonium Phosphate	T	T
8	Ammonium Sulfate	T	T
9	Aqua Regia	T	T
10	ASTM Fuel A (=Isooctane)	A	A
11	ASTM Fuel B	B	B
12	ASTM Fuel C	B	B
13	ASTM Fuel F (=Diesel)	A	A
14	Benzene (99.5%)	C	C
15	Calcium Chloride (30%)	A	A
16	Calcium Chloride Solutions	T	T
17	Calcium Hydroxide	T	T
18	Chlorine solution (0.3%)	C	C
19	Corn oil	A	A
20	Cyclohexane	B	B
21	Ethanol (=Ethyl Alcohol)	A	A
22	Ethyl acetate	C	C
23	Ethylene Glycol4	A	A
24	Furfural	T	T
25	Gasoline	B	B
26	Glycerins	A	A
27	Hydrochloric acid (10%)	A	A
28	Hydrochloric acid (36%)	C	C
29	Isopropyl alcohol	A	A
30	Ivory Soap	A	A
31	Kerosene	A	A

No	Chemical	DREAMLINER 30	DREAMLINER 28
32	Lactic acid	A	A
33	Linseed oil	A	A
34	Magnesium Chloride	T	T
35	Magnesium Hydroxide	T	T
36	Methanol	A	A
37	Methyl ethyl ketone	C	C
38	Methylene chloride	C	C
39	Mineral spirits	A	A
40	Naptha	A	A
41	Nitric acid (5%)	A	A
42	Nitric acid (50%)	C	C
43	Perchlorethylene	B	B
44	Phenol	C	C
45	Phosphoric acid (50%)	A	A
46	Phosphoric acid (85%)	C	C
47	Phthalate plasticiser	C	C
48	Salt water (25%)	A	A
49	Sea water	A	A
50	Sodium Acetate Solutions	T	T
51	Sodium Bisulfite Soutions	T	T
52	Sodium hydroxide (40%)	C	C
53	Sodium phosphate	A	A
54	Sulphuric acid (50%)	A	A
55	Sulphuric acid (97%)	B	B
56	Tannic acid (10%)	C	C
57	Tannic acid (40%)	C	C
58	Tetrahydrofuran	C	C
59	Toluene	C	C
60	Turpentine	A	A
61	Vegetable oil	A	A
62	Xylene	C	C

Ratings :

A	Little or no effect
B	Somewhat effect
C	Severe effect
T	Likely to be severe effect

