



INTERSTATE PRODUCTS, INC.

6561 Palmer Park Circle Suite A
Sarasota, FL 34238

PH: 800-474-7294 store.interstateproducts.com Fax: 800-448-6329

Technical Data Sheet

Traction-N-More

Product Number: TZ-20-22-6 & TZ-20-22-M-6

DESCRIPTION:

Traction-N-More WB is an advanced formula, two-component epoxy amine coating system with excellent performance characteristics. **Traction-N-More WB** works well in factories, warehouses, schools, hospitals, electronic, food processing and pharmaceutical applications.

ADVANTAGES:

Traction-N-More WB is low odor and non-flammable allowing this material to be applied without evacuating personnel in most cases. **Traction-N-More WB** imparts a high gloss, durable abrasion resistant coating that is washable and chemically resistant. Because of the low VOC content, **Traction-N-More WB** adheres to most previous coatings. It is a good practice to apply a small sample over unknown material to check adhesion.

APPLICATION:

Highly dense or steel toweled concrete should be cleaned and etched with **Tuffclean**. Previously coated surfaces should be cleaned and degreased with **Permaclean**.

Mix Ratio: 4 Parts Mix A to 1 Part Mix B

Pot Life: Approximately 4 to 6 Hours at 75 degrees F

Drying Time: 2 Hours Tack Free-Overnight for light traffic

Priming: On unprimed concrete surface thin first coat 5 to 10% with water.

Finish: Apply mixed products as supplied with no thinning.

Technical service is available for any questions.

Do not add any solvent or other materials to this product. Traction-N-More WB exhibits an equivalent chemical resistance to similar conventional solvent epoxy systems.

Do not apply when temperature of substrate is below 45 degrees F.

CLEAN UP:

Clean tools and equipment with water immediately after use.

PACKAGING:

1.25 Gal. Unit: 1 Gal. Mix -A, 1 Qt. Mix -B