

Revision Date: 3-22-21

**Ref:** 10-15-19

By: LSR

## **TECHNICAL DATA SHEET**

## L3790NESUE-REVB

## 1.0 BASE FABRIC

1.1	Base Fabric Weight	15.6	oz/yd²	529	g/m²				
2.0 COATED FABRIC									
2.1	Total Weight	37 -1/+2	oz/yd²	1,254	4 -34/+68 g/m <sup>2</sup>				
2.2	Coating Type		Uretha	ine					
2.3	Sealing Properties		Dielectric	⊠ T	hermal				

3.0 MATERIAL PROPERTIES		<u>Standard</u>		<u>Met</u>	ric	ASTM TEST METHODS
3.1	Tensile Strength, 1" Strip					
	Warp Fill	700 700	lbs lbs	3,113 3,113	N N	D751-B
3.2	Tensile Elongation, 1" Strip					
	Warp Fill	25 25	% %	25 25	% %	D751-B
3.3	Tear Strength, Tongue					
	Warp Fill	50 50	lbs lbs		N N	D751-B (mod)
3.4	Puncture, Screwdriver	225	lbs	1,000	N	D751
3.5	Puncture, Ball	1,800	lbs	8,000	N	D751
3.6	Hydrostatic Resistance	600	psi	4.1	MPa	D751-A
3.7	Adhesion, RF	50	lbs/in	88	N/cm	D751
3.8	Adhesion, Thermal	50	lbs/in	88	N/cm	D751
3.9	Low Temp	-50	°F	-46	oC	D2136
3.10	High Temp, Cont/Interm.	160 / 180	°F	71/82	oC	D1204

COMMENTS: This product is designed for primary containment of fuel in accordance with MIL-PRF-32233B (Rev May 2015).

This product is made with thermoplastic urethane (TPU) resin that is NSF 61 certified for potable water storage.

A variety of standard widths and colors are available. Contact Cooley Engineered Membranes for details.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.